

TECHNICAL BULLETIN

TOPLINE W FOR STEEL

Product Description: *TOPLINE W* is a three component, powder filled Bisphenol-A-vinyl ester lining system. This system consists of one trowel applied body coat, a 300 g/m² fibreglass mat as reinforcement and a trowel applied special filled resin topcoat to produce a total DFT of 3.0 – 4.0 mm nominal.

Recommended Uses: This high performance lining system possesses outstanding resistance to a wide range of aggressive environments such as limestone slurry, gypsum and other suspensions. It is designed especially for the protection of concrete against the attack of abrasive reagents.

Temperature Resistance: + 75 °C wet

Generic Type: Bisphenol-A- Vinyl Ester

Filler: Silica and Aluminium Oxide

Solvent: Styrene (reactive)

Design: The steel construction to be coated must be fabricated according to the DIN EN 14879-1:2005. Further information can be taken from our steel specification documents.

Preparation: Steel
Steel substrates, which were under service conditions already, require a chemical check for the presence of invisible traces of iron sulphate and or iron chloride. If the check is positive, the total surface area needs to be washed down thoroughly with de-ionised water. In each case, steel substrate shall be prepared by abrasive blasting to obtain a Sa 2½ surface, as defined in DIN EN ISO 12 944-4 and a minimum surface profile @ 60 µm "Coarse (G)" as defined in DIN EN ISO 8503-2.

Build-up of the system:		Coverage
COROFLAKE N PRIMER	Liquid + HARDENER No. 1	150 g/m ²
<i>TOPLINE W</i> Body Coat	Liquid + HARDENER No. 1 F-1 Filler	1,000 g/m ² 2,400 g/m ²
<i>TOPLINE W</i> Reinforcement	Liquid + HARDENER No. 1 Glass mat 300 g/m ²	660 g/m ² 330 g/m ²
<i>TOPLINE W</i> Topcoat	Liquid + HARDENER No. 1 W-1 Filler Smoothing Liquid F-12	1,000 g/m ² 2,600 g/m ² 150 g/m ²

Mixing Ratio: 100:2 resin to hardener by weight. Mix hardener into liquid using a low speed mechanical agitator. For body coat, stir 2,400 g of the silica filler slowly into the 1,000 g of the mixed resin until it becomes a well dispersed semi-thixotropic mortar. For the topcoat, instead of F1 filler add 2,600 g W1 filler.



Pot Life:	1 ½ hrs. (+ 10 °C)	1 hr. (+ 20 °C)	½ hr. (+ 30 °C)
Application Equipment:	By Trowel and Roller.		
Application:	During application observe pot life limitations. Note: During application the lined surface must be shaded from direct or indirect sunlight. Otherwise intercoat disbondment may occur. Refer to the application instruction for further hints.		
Cleaning:	Solvent T-100		
Shelf Life:	The shelf life is 6 months when stored @ + 20 °C. The lining liquid, primer and hardener should be stored in cool and dry places.		
Density:	1.85 kg/l (mixed with filler)		
Viscosity:	semi thixotropic		
Flash Point:	TOPLINE W resin	+ 32 °C and	
	HARDENER No. 1	+ 70 °C	
Modulus of Elasticity:	7,000 – 10,000 MPa (DIN EN ISO 178) flexural		
Tensile Strength:	20 Mpa (DIN EN ISO 527)		
Compressive Strength:	85 MPa (DIN EN ISO 604)		
Coefficient of Expansion:	27 - 30 x 10 ⁻⁶ 1/°C (ASTM D 696-90)		
Abrasion:	30 mg (ASTM – D 4060)		
Permeation:	0.0031 perm-inch (ASTM – E 96 - 90 Procedure E)		
Adhesion:	7.0 MPa (EN ISO 4624)		
Hardness:	35 Barcol (DIN EN 59)		

This Technical Bulletin is for informational purposes only. All data provided herein is based on in-depth research and testing, however no liability whatsoever can be assumed. Since we are constantly endeavouring to up-date and improve our products, we recommend noting the index and issue date indicated on this data sheet and to inquire as to whether any properties have changed in the interim. This Product Information Sheet replaces all prior issues. Please contact our Technical Consultant for detailed information in case of ambiguities.

TIP TOP Oberflächenschutz Elbe GmbH, Heuweg 4, D-06886 Wittenberg
Telefon: (0 34 91) 6 35 – 50, Telefax: (0 34 91) 6 35 – 5 52

TIP TOP Oberflächenschutz Elbe GmbH	TOPLINE W FOR STEEL	INDEX C of 10.02.2006
Page: 2/2	ATB	Replace Issue: 01.01.2005